

PRODUCT DATA SHEET

EAJ 1 EP/220 WHEEL BEARING EP GREASE NLGI 2

AUTOMOTIVE GRADE

GENERAL PURPOSE EP GREASE

Product Description

This is a general purpose EP grease for use in general automotive and industrial applications. The lubricating ability of EAJ 1 EP/220 was made from high quality pure base oil, imported thickener and additive from USA.

With the unique combination of reacting lime and lithium, it gives better performance especially in water resistances and enable the grease to be pumped equally well at low or high temperature. It can withstand temperature up to $180 \,^{\circ}$ C / $356 \,^{\circ}$ F.

Product Application

EAJ 1 EP/220 is recommended for most heavy vehicles, machineries and for general lubrication. High temperature performance at affordable price. Suitable for most bearing applications as it can withstand higher temperature than normal heavy grease.

TYPICAL PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	TYPICAL VALUES
NLGI GRADE	ASTM D-217	2
WORKED PENETRATION @ 25°C / 77°F	ASTM D-217	265 - 285
APPEARANCE	ROOM TEMP.	Soft
THICKENER/ SOAP TYPE	-	Melting Base
STRUCTURE	-	Smooth
COLOUR	VISUAL	Red
BASE OIL VISCOSITY cSt at 100°C (212°F)	ASTM D-445	Min. 15
DROPPING POINT	ASTM D-2265	180°C / 356°F +/- 5
VISCOSITY INDEX	ASTM D-2270	Min. 95
WATER RESISTANT	-	Good
TIMKEN OK LOAD, LBS	ASTM D-2509	Approx. 35
4-BALL EP WELD LOAD, KGS	ASTM D-2596	Approx. 230

TEMPERATURE RANGE	CAUTION:
For continuous service is -20°C to 120°C [-4°F to 248°F]	Do not ingest! If this should occur, drink large volumes of water And seek medical attention. Always keep container sealed when not in use. Keep out of reach of children.
With frequent re-lubrication up to 135°C [275°F]	

This information is our best knowledge, true & accurate, subjected to change without prior notice due to continual product research and development. All recommendations or suggestions are without guarantee since the conditions of use are beyond our control. The manufacturers do not accept liability for any loss or damage, however arising, which results directly from the use of such information, nor do we offer any warranty of immunity against patent infringement.

